

# MAXBERG® JURA KALKSTEIN GETROMMELT *Palazzo*®

## JURA-KALKSTEIN GELB, GETROMMELT

<b>PETROGRAPHISCHE BEZEICHNUNG</b>	Kalkstein
<b>PETROGRAPHISCHE BESCHAFFENHEIT</b>	Bräunlich-gelber Kalkstein mit einzelnen ockerfarbenen Einlagerungen. Bedingt durch den Trommel-Vorgang zeigen sich die Kanten antik, die Plattenoberfläche hell.
<b>GEOLOGISCHE FORMATION</b>	Jura
<b>VORKOMMEN</b>	Gebiet um Treuchtlingen
<b>VERWENDUNG</b>	Innenbeläge, Spezialanfertigungen auf Anfrage

## TECHNISCHE DATEN

Rohdichte nach DIN EN 1936	2,450 - 2,602 g/cm <sup>3</sup>
Druckfestigkeit nach DIN EN 1926	Mittelwert 136,6 MPa
Abriebwiderstand nach DIN EN 14157/B ("Böhme")	Mittelwert 17,7 cm <sup>3</sup> / 50 cm <sup>2</sup>
Abriebwiderstand ("Capon") nach DIN EN 14157	Mittelwert 18,9 mm

# MAXBERG® JURA LIMESTONE TUMBLED *Palazzo*®

## JURA-LIMESTONE BEIGE, TUMBLED

<b>PETROLOGIC CLASSIFICATION</b>	Limestone
<b>PETROLOGIC CONDITION</b>	Limestone brown-beige, with some brown inclusions. As a result of the tumbling process, the edges are antique and the surface colour light.
<b>GEOLOGICAL FORMATION</b>	Jurassic
<b>QUARRY LOCATION</b>	Area around Treuchtlingen, North Bavaria / Germany
<b>USE</b>	Internal paving, special items on enquiry.

## TECHNICAL DATA

Density according DIN EN 1936	2,450 - 2,602 g/cm <sup>3</sup>
Compressive strenght according DIN EN 1926	mean value 136,6 MPa
Abrasion resistance according DIN EN 14157/B ("Böhme")	mean value 17,7 cm <sup>3</sup> / 50 cm <sup>2</sup>
Abrasion resistance ("Capon") according DIN EN 14157	mean value 18,9 mm

